TECHNICAL DATA

Consistency	: Thick and Buttery
Thinner	: Municipal/ Potable Water
Method of Application	: Brush/ Roller
Spreading Capacity	: 140-160 sq. ft./ ltr./ 2 coats
	(Actual coverage may vary depending on method, condition of application, surface porosity & shade)
Drying Time	: Surface dry time 15-25 minutes
Finish	: High Sheen/ Superior Finish
Shades Available	: As per shade card (Refer to Colormenu Fendeck)

GLAMOUR ADVANCED
ANTI STAIN

LEAD CONTENT DOES NOT EXCEED 90PPM*
For a Healthy Future
*90 parts per million

Indian Green Building Council MEMBER

GRIHA

British Paints Glamour Anti Stain Interior Emulsions is a water-based acrylic emulsion with the stain-resistant formula which is characterized by high sheen, excellent washability, superior finish, levelling, opacity and comes with a long-lasting finish.

H_2O
WATER BASED

PRODUCT FEATURES

Advanced Stain Resistant Formula

Excellent Washability

Anti-Bacterial & Anti-Fungal

Elastomeric

High Sheen & Superior Finish

PACKS AVAILABLE

1 LTR   4 LTR   10 LTR   20 LTR

HOW TO APPLY

Performance of Glamour Advanced Anti Stain depends on surface preparation & application as outlined below.

SURFACE PREPARATION
Sand the surface with emery paper no. 180 to remove loose particles, paint, dust, cracked & flaked paint and wipe clean.

PRIMER
Apply a coat of British Paints Solvent Thinnable Primer or Water Thinnable Supra Acrylic Cement Primer (For repainting use Water Thinnable Supra Acrylic Cement Primer and for new surface Solvent Thinnable Primer is recommended) and allow drying for 6-8 hours.

PUTTY
Smoothen the surface by filling dents with a thin coat of British Paints Acrylic Wall Putty and allow drying for 4-6 hours. Sand the surface with emery paper no. 180 and wipe clean.

PRIMER
Apply another coat of British Paints Solvent Thinnable Primer or Water Thinnable Supra Acrylic Cement Primer and allow drying for 6-8 hours. Sand the surface with emery paper 320 and wipe clean.

TOP COAT
Thin 1 litre of Glamour Advanced with 500 - 600 ml of water. Apply 2-3 coats of this thinned paint with a gap of 3-4 hours in between 2 coats.

(The information herein is given in good faith. Covering capacity is indicated on the basis of results obtained on a prepared smooth surface)

(Please note that this product technical data sheet supersedes all previous versions.)