

SATIN ADVANCED ENAMEL

British Paints Satin Advanced Enamel is a premium quality matt enamel which gives your surfaces a soft sheen finish. It's opaque, washable film combined with a high covering capacity and matchless durability offers an excellent look and feel to your surface. Recommended for both interiors and exteriors on wood, metal & cement plaster surfaces.



TECHNICAL DATA

Areas of Application	: Metals / Wood / Masonry Surfaces
Viscosity of Supply	: 95 ± 10 Secs / F4 / 30°C
Thinner Recommended	: British Paints Synthetic Thinner
Recommended Primer For Metal	: British Paints Red Oxide Primer/ British Primer Solvent Thinnable White Primer
For Wood	: British Paints Wood Primer White or Pink
For Masonry	: British Paints Solvent Thinnable Primer
Method of Application	By Brush or Roller. During application viscosity is to be adjusted suitably depending on the nature of surfaces and ambient temperature conditions by recommended thinner
Covering Capacity (Spreading by brush on smooth metal surfaces)	: 160-180 sq. ft. at DFT of 25-30 Micron per ltr. per coat : 110-130 sq. ft. / ltr. / 2 coat at DFT of 40- 50 M
Drying Time	: SURFACE DRY - Max 3 Hrs. (28-30°C RT & 60 ± 5 R.H.) HARD DRY - Within 18 Hrs.
Finish	: Smooth with Soft Sheen
Flash Point	: Above 35°C (Abel's closed cup)
Shades Available	: Brown, Black, Mahogany, Teak Special, Black Rose. Also available in White and Base White
Packs Available	: 20 ltr, 10 ltr, 4 ltr, 1 ltr & 500 ml

DIRECTIONS FOR USE

- The surface to be painted should be free from rust, grease, oil, loose particles etc and should be dry.
- All surfaces (including old painted surface where paint film is firmly adherent) should be thoroughly rubbed with suitable sand paper and thereafter wiped off.
- In case of new or bare surfaces, prime the surfaces with recommended primer. Use Knifing Paste Filler to fill up dents or any surface imperfections. Sand the primed surface with suitable sand paper and if Knifing Paste Filler is used, a coat of British Paints Solvent Thinnable Primer is recommended.
- Apply two coats of Satin Advanced Enamel giving 18hrs. of drying between coats.
- Thinning is normally not required but if necessary it can be thinned suitably with recommended thinner.
- Normally two coats are sufficient for right opacity and finish but if strong colour change is required one more coat is recommended.

(The information herein is given in good faith. Covering capacity is indicated on the basis of results obtained on a prepared smooth surface).

