

# MASTERBLASTER INTERIOR EMULSION

British Paints MasterBlaster Interior Emulsion is a super economy water thinnable washable coating for application on interior surfaces and provides a rich smooth finish near to the price of Distemper. MasterBlaster outperforms conventional distempers in all respects be it durability, hiding, covering capacity, finish etc.



## TECHNICAL DATA

Areas of application	: Interior Plasters, Asbestos Sheets, Brick Work and Concrete
Viscosity of supply	: 100-116 Krebs units on stormer viscometer at 30°C
Recommended thinner	: 50-60% by volume with water
Method of application	: Brush / Roller
Covering capacity (spreading by brushing)	: 90-100 sq. ft. / ltr in 2 coats depending on surface smoothness / surface absorption
Drying time	: Surface dry 20-30 minutes (@28-30°C & 60 ± 5% R.H.)
Re-coating period	: About 4-5 Hrs.
Finish	: Smooth and Matt
Shades available	: As per shade card / Also available in White
Packs available	: 20 ltr, 10 ltr, 4 ltr & 1 ltr

## DIRECTIONS FOR USE

**SURFACE PREPARATION:** Newly plastered surface must be allowed to mature for a minimum period of six months. The surface should be sanded with emery paper no. 180 to remove loose particles, paint, dust, cracked & flaked paint and wipe clean.

**PRIMER:** Apply a coat of British Paints solvent thinnable primer or water thinnable Acrylic Cement Primer (For repainting use water thinnable Acrylic Cement Primer and for new surface solvent thinnable primer is recommended) and allow drying for 6-8 hours.

**PUTTY :** Smoothen the surface by filling dents with a thin coat of British Paints Acrylic Wall Putty and allow drying for 4-6 hours. Sand the surface with emery paper no. 180 and wipe clean.

**PRIMER :** Apply another coat of British Paints solvent thinnable primer or water thinnable Acrylic Cement Primer and allow drying for 6-8 hours. Sand the surface with emery paper no. 320 and wipe clean.

**TOPCOAT:** Thin 1 litre of MasterBlaster Interior Emulsion with 500-600 ml of water. Apply 2-3 coats of this thinned paint with a gap 3-4 hours in between two coats.

**STIR WELL BEFORE USE.**

(The information herein is given in good faith. Covering capacity is indicated on the basis of results obtained on a prepared smooth surface).

MASTERBLASTER INTERIOR EMULSION

